



CURLEX® II (.98) FIBRENET™ MATERIAL SPECIFICATIONS

Materials:

Great Lakes Aspen (naturally seed free)
Biodegradable Jute Netting
QuickGRASS® (green excelsior – optional)

Typical Roll Sizes:

Width:	4.0 ft (1.2 m)	8.0 ft (2.4 m)
Length:	90.0 ft (27.4 m)	90.0 ft (27.4 m)
Area:	40.0 yd ² (33.4 m ²)	80.0 yd ² (66.9 m ²)
Weight:	39.2 lb (17.8 kg)	78.4 lb (35.6 kg)

Description:

Curlex II .98 FibreNet erosion control blanket (ECB) is a natural, stitched excelsior blanket with 100% biodegradable Jute netting that provides a temporary organic cover to reduce erosion, protect seeds, enhance germination, and hasten re-vegetation. Product is 100% biodegradable. Curlex II .98 FibreNet is furnished in rolls with polyethylene wrapping to protect against the elements prior to installation, and may be ordered in Master-Paks of fifteen rolls banded together to minimize material handling requirements. Curlex II .98 FibreNet is also available as *QuickGRASS®* (Dyed Green). ECB shall be Manufactured in the U.S.A.

Curlex II .98 FibreNet has a design soil loss ratio (event-based RULSE C factor) of .022 and is typically suitable for slopes up to 1:1. Curlex II .98 FibreNet is rated for channel flows up to 9.5 ft/s (2.9 m/s) and 2.5 lb/ft² (120 Pa) shear stress.

Physical Properties:

Fiber: Great Lakes Aspen (naturally seed free)
Curled, interlocking fibers with barbed edges

Fiber Size: 80% of fibers a minimum of 6” (15.2 cm) long
0.038” ± 0.008” wide x 0.018” ± 0.003” thick
(0.97 mm ± 0.20 mm wide x 0.46 mm ± 0.08 mm thick)

Weight*: 0.98 lb/yd² (0.53 kg/m²) ± 10% @ 22% Moisture

Thread Pattern: No more than 4.0” (10.2 cm) transverse stitch spacing

Net Material: Biodegradable Jute

Net Openings: ≈ 0.50” wide x 0.50” long (12.7 mm x 12.7 mm)

Net Configuration: Top and bottom

* Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%.





MANUFACTURER'S CERTIFICATION

CURLEX® II (.98) FIBRENET™ - Erosion Control Blanket

Manufacturer:

American Excelsior Company
831 Pioneer Avenue
Rice Lake, WI 54868
1-866-9FIBERS (1-866-934-2377)

Project Information (if applicable):

Name:

Location:

Number:

Statement

We hereby certify that the above referenced material is manufactured to meet or exceed the following specification:

Fiber:	Great Lakes Aspen (naturally seed free) Curled, interlocking fibers with barbed edges
Fiber Size:	80% of fibers a minimum of 6" (15.2 cm) long 0.038" ± 0.008" wide x 0.018" ± 0.003" thick (0.97 mm ± 0.20 mm wide x 0.46 mm ± 0.08 mm thick)
Blanket Length:	-0' (m) + 2.0' (0.6 m)
Blanket Width:	-0" (mm) + 1.0" (25.4 mm)
Weight*:	0.98 lb/yd ² (0.53 kg/m ²) ± 10% @ 22% Moisture
Thread Pattern:	No more than 4.0" (10.2 cm) transverse stitch spacing
Net Material:	Biodegradable Jute
Net Openings:	≈ 0.50" wide x 0.50" long (12.7 mm x 12.7 mm)
Net Configuration:	Top and bottom

* Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%.



Tony Johnson – General Manager, Rice Lake

10/12/11
Effective Date

Note: This Certification expires, without notice, if document is updated by American Excelsior Company (AEC). Current Material Specifications and Manufacturer's Certifications (MSMC) for AEC products shall be accessed from www.Curlex.com at all times.

