



## CURLEX® II CL MATERIAL SPECIFICATIONS

### Materials:

Great Lakes Aspen (naturally seed free)  
Polypropylene Netting  
Stitching Thread

### Typical Roll Sizes:

Width:	4.0 ft (1.2 m)	8.0 ft (2.4 m)	12.0 ft (3.7 m)	16.0 ft (4.9 m)
Length:	150.0 ft (45.7 m)	150.0 ft (45.7 m)	150.0 ft (45.7 m)	150.0 ft (45.7 m)
Area:	66.7 yd <sup>2</sup> (55.7 m <sup>2</sup> )	133.3 yd <sup>2</sup> (111.5 m <sup>2</sup> )	200.0 yd <sup>2</sup> (167.2 m <sup>2</sup> )	266.7 yd <sup>2</sup> (223.0 m <sup>2</sup> )
Weight:	33.4 lb (15.1 kg)	66.7 lb (30.3 kg)	100.0 lb (45.4 kg)	133.4 lb (60.5 kg)

### Description:

Curlex II CL erosion control blanket (ECB) is a natural, stitched excelsior blanket that provides a temporary organic cover to reduce erosion, protect seeds, enhance germination, and hasten re-vegetation. Curlex II CL is furnished in rolls with polyethylene wrapping to protect against the elements prior to installation, and may be ordered in Master-Paks of fifteen rolls banded together to minimize material handling requirements. ECB shall be Manufactured in the U.S.A.

Curlex II CL has a design soil loss ratio (event-based RUSLE C factor) of .050 and is typically suitable for slopes up to 1.5:1. Curlex II CL is rated for channel flows up to 7.3 ft/s (2.2 m/s) and 1.80 lb/ft<sup>2</sup> (86 Pa) shear stress.

### Physical Properties:

Fiber: Great Lakes Aspen (naturally seed free)  
Curled, interlocking fibers with barbed edges

Fiber Size: 80% of fibers a minimum of 6" (15.2 cm) long  
0.038" ± 0.008" wide x 0.018" ± 0.003" thick  
(0.97 mm ± 0.20 mm wide x 0.46 mm ± 0.08 mm thick)

Weight\*: 0.50 lb/yd<sup>2</sup> (0.27 kg/m<sup>2</sup>) ± 10% @ 22% Moisture

Thread Pattern: No more than 4.0" (10.2 cm) transverse stitch spacing

Net Material: Polypropylene (green with oxo-biodegrader additive or white with UV degrader additive)

Net Openings: 1.0" wide x 2.0" long (25.4 mm wide x 50.8 mm long)

Net Configuration: Top and bottom

\* Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%.





## MANUFACTURER'S CERTIFICATION

### **CURLEX® II CL - Erosion Control Blanket**

#### Manufacturer:

American Excelsior Company  
831 Pioneer Avenue  
Rice Lake, WI 54868  
1-866-9FIBERS (1-866-934-2377)

#### Project Information (if applicable):

**Name:**

**Location:**


**Number:**

#### Statement

We hereby certify that the above referenced material is manufactured to meet or exceed the following specification:

Fiber:	Great Lakes Aspen (naturally seed free) Curled, interlocking fibers with barbed edges
Fiber Size:	80% of fibers a minimum of 6" (15.2 cm) long 0.038" ± 0.008" wide x 0.018" ± 0.003" thick (0.97 mm ± 0.20 mm wide x 0.46 mm ± 0.08 mm thick)
Blanket Length:	-0' (m) + 2.0' (0.6 m)
Blanket Width:	-0" (mm) + 1.0" (25.4 mm)
Weight*:	0.50 lb/yd <sup>2</sup> (0.27 kg/m <sup>2</sup> ) ± 10% @ 22% Moisture
Thread Pattern:	No more than 4.0" (10.2 cm) transverse stitch spacing
Net Material:	Polypropylene (green with oxo-biodegrader additive or white with UV degrader additive)
Net Openings:	1.0" wide x 2.0" long (25.4 mm wide x 50.8 mm long)
Net Configuration:	Top and bottom

\* Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%.

  
\_\_\_\_\_  
Tony Johnson – General Manager, Rice Lake

12/16/10  
Effective Date

**Note:** This Certification expires, without notice, if document is updated by American Excelsior Company (AEC). Current Material Specifications and Manufacture's Certifications (MSMC) for AEC products shall be accessed from [www.Curlex.com](http://www.Curlex.com) at all times.

